

Halo SV Auto-Revive

HALO SURFACES INTERNATIONAL LIMITED



Surface Preparation Instructions

The surface must be clean, dry and in sound condition. Remove all oil, dust, grease and dirt using **Halo Degreaser**. Rinse thoroughly with fresh water and allow to dry. Mask off all areas that are not to be coated and cover the driveway or garage floors next to the tyres to protect them from drips.

Application Instructions

TEST: Because there are many differences in substrates always test **Halo SV Auto-Revive** in an inconspicuous area to ensure compatibility and performance.

APPLICATION: Apply **Halo SV Auto-Revive** in an ambient temperature between 7-40 degrees Celsius, 90% RH or less, and, if applying outdoors make sure that there will be no rain or dew for 5 hours after completing the coating process.

THOROUGHLY STIR the contents of the container for several minutes (or shake it thoroughly if the container is a small one). This re-suspends the nano particles and is vital for proper performance of the coating. Re-stir or re-shake the container every 15-20 minutes to ensure the nano particles remain suspended.

Use a soft lint-free paper towel or cloth to apply **Halo SV Auto-Revive**. Saturate the towel with product (don't let it drip) and wipe a thin coat onto the surface. Avoid streaks. Some surfaces, such as tyres, may take several coats to fill in the damaged oxidized rubber. Wait 5-10 minutes between coats but not more than 10 minutes.

Keep the lid on the tin to stop evaporation.

Drying time

At 21 degrees Celsius 50% RH : Touch dry – 1 hour; dry through 2-4 hours; full cure 7 days.

Cleaning Up

Clean tools and equipment immediately with acetone.

Care and Maintenance

To clean exterior surfaces, hose with water. For interior surfaces use a damp cloth or towel. If additional cleaning is required use **Halo Green Cleaner**. Rinse off with fresh water and dry. To re-apply, follow the application instructions. There is no need to strip off the original coat.

Product Characteristics

Colour: Slight amber to rose in the tin but dries clear.

Finish: Semi-gloss

Base Material: Solvent

Flash Point: 16.7C (C Pensky-Martens Closed Cup)

VOCs: 20g/L

Weight: 880 gms/L

Non-breathable

Coverage

10 sq m per 500 mls (depending on texture and porosity).

Durability

6 months to 1 year. Then simply reapply as required.

Product Description

Halo SV Auto-Revive is a very thin strong coating formulated using the principles of **Halo Matrix-Nano™** controlled chemical nanotechnology. It is designed to penetrate the surface of rubber tyres, hoses, shock-absorber covers and plastic and vinyl dashboards and trims. It restores the original colour and lustre of surfaces damaged by UV exposure and protects them from further damage.

Use on these substrates

Rubber tyres, engine hoses, rubber, vinyl and plastic trim and shock-absorber covers.

Solve these problems

Halo SV Auto-Revive will restore oxidized, discoloured and damaged rubber, plastic and vinyl auto parts, and will provide protection from future UV damage.

Halo SV Auto-Revive will not restore surfaces where the original pigment is too low.

COATINGS from Halo Surfaces International Ltd are sensitive to the environment.

Halo SV Auto-Revive enhances tyres and dashboards for months not days



Warnings

FLAMMABLE LIQUID: contains TBA and Ethyl Alcohol.

If in an enclosed area you must have fresh air supply and exhaust.

You must wear an approved respirator.

Wear butyl-rubber gloves.

Wear safety goggles. Do not rely on contact lenses to protect eyes.

Avoid open flames and ignition sources. The fumes are flammable.

If splashed on skin, wash thoroughly with soap and water.

If coating gets into eyes, flush with water for 15 minutes. If irritation continues obtain medical attention.

If swallowed, rinse mouth with water and obtain immediate medical attention.

Hazmat Information

Coating Solution UN#1139, Class 3, Packing Group III.

Warranty

Halo Surfaces International Ltd guarantees **Halo SV Auto-Revive** to be defect-free. All material proven defective will be replaced within 1 year of date and proof of purchase. The warranty is for defective product only and does not cover wear and tear or application not carried out in accordance with these instructions and any other related guidelines on the company's **website www.halosurfaces.com**.

This warranty is given in lieu of all other warranties, express or implied including warranty of merchantability or fitness for purpose.

The remedy contained in this warranty is an exclusive remedy and **Halo Surfaces International Ltd** shall not be responsible for any other damages including labour or any incidental, consequential, special or punitive damages whatsoever.